


Intensive Glass Beads

Silicate of boron grinding glass beads has features of tenacity, wear resistance, steady chemical change and 7.2 PH-value are suitable both for grinding materials with low, middle adhesion and blasting processes.



★ **Ordering information:**

BGD 1320---Intensive Glass Beads (25 KG/package)

Main Technical Parameters:

★ Chemical composition:

SiO_2 Al_2O_3 CaO BaO Na_2O B_2O_3

★ Proportion: 2.5g/cm^3

★ Artificial Proportion: 1.5g/cm^3

★ Micro-rigidity: $\geq 680\text{kg/mm}^2$

★ Diameters: 0.6–0.8mm; 0.8–1.0mm; 1.0–1.5mm;
1.5–2.0mm; 2.0–2.5mm; 2.5–3.0mm;
3.0–3.5mm;